



RUSTIN RESIN

PRODUCT DATA SHEET

RS-1010-GENERAL PURPOSE ECONOMIC ROOFLIGHT RESIN

Applications:

This resin is especially designed for the manufacture of roofing sheets

Properties:

Low viscosity and Medium Reactivity

Excellent clarity and transparency.

Stable gel time.

Composition of the Resin:

RS-1010 is General purpose unsaturated Polyester resin having low viscosity and medium reactivity based on Orthophthalic acid and standard glycols, dissolved in styrene monomer. It is specially designed for the manufacture of roofing sheets. The roofing sheets clarity made with this resin and powder bonded mat is inferior and transparent.

Compatibility:

Avoid storing the resin along with Metallic Driers, Peroxides and catalyst in the same area.

Safety:

Material Safety Datasheets of the product is available on demand.

Product Data:

PARAMETERS	UNIT	SPECIFICATIONS
Appearance		Clear Transparent Liquid
Color		≤ 1
Viscosity @25°C LV#2,30 RPM	Cps	200± 25
Acid Value	Mg.KOH/gm	15 ± 5
Specific Gravity@25°C	Gm/ml	1.12±0.02
Volatile content	%	35±3
Gel time @25°C	Min	5-7
Peak exotherm temperature	°C	180

Gel Time with 1.0ml Cobalt Octate (Metal content 3%) and 1.5ml MEKP (Active Oxygen 9 ± 0.2)@25°C

Storage Conditions:

RS 1010 should be stored in a cool and dry place away from sunlight and other sources of heat, preferably below 25°C. At higher storage temperatures, the shelf life decreases sharply. Presence of moisture also affects the storage life of the resin leads to turbidity in the resin.

Stability:

On storage under above mentioned conditions, the stability for RS 1010 is guaranteed for 3 months

Supply Modes:

Resin is supplied in 200 kgs Steel Drums.

Food and Drug:

All resins in this datasheet are manufactured from raw materials that are listed in FDA regulation Title 21 CFR 177.2420.

Mechanical Properties of Clear Cured Castings:

PROPERTIES	TEST VALUE	METHOD
Barcol Hardness	40	ASTM D2583
Tensile Strength (MPa)	45	ISO 527-2
Flexural Strength (MPa)	90	ISO178
Elongation at Break	3	ISO 527-2
Heat Distortion Temperature (°C)	58	ISO75-2
Water Absorption @25°C(after 24 Hrs.) mg	28	ISO 62

Curing Conditions:

The specimens for testing of mechanical properties are prepared by curing the resins with 0.5 ml Accelerator (3% cobalt content) and 1.0 % MEKP catalyst, added to 100 gm. of resin. The specimens are cured for 24 hours at room temperature followed by post curing for 4 hours at 80°C.

Disclaimer:

Although the facts and suggestions in this data sheet are based on our own research and are believed to be reliable, we cannot assume any responsibility for performance or results obtained through the use of our product described herein in view of the many factors that may affect processing and application.

RUSTIN RESIN does not guarantee duplication of such results by third parties.

Method of Testing:

The method of testing and the tolerances are as prescribed in ISO, ASTM and BS where is not available.

Contact us:

Tel: 00982188936500 Fax: 00982188944475 Website: www.rustinco.ir Email: info@rustinco.ir

**** Gel time, Acid value and viscosity can be adjusted as per customer requirements.**