	TYPICAL DATA SHEET*	ISSUE DATE	Feb-15
	GRADE	WWW.TPCO.IR	
	LL0220AA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984114282612	

LL0220AA is linear low density polyethylene copolymer containing butene-1(C4) as comonomer.It is suitable for blending with conventional LDPE for cast film applications.

Film made from pure LL0220AA has the following advantages over LDPE:

good balance of mechanical properties,good optical properties

Applications:

light and medium duty films,stretch film

PROPERTY	UNIT	TEST METHOD	TYPICAL VALUE
MELT FLOW INDEX(2.16KG)	g/10min	ASTM D-1238	2.4
DENSITY	gr/cm3	ASTM D-1505	0.921
VICAT SOFTENING POINT	°C	ASTM D-1525	100

FILM**


PROPERTY	METHOD A	GR	TEST METHOD	TYPICAL VALUE
DART DROP IMPACT			ASTM D-1709	90
TENSILE STRESS AT YEILD	MD/TD	MPA	ASTM D-882	10/11
TENSILE STRESS AT BREAK	MD/TD	MPA	ASTM D-882	30/25
ELONGATION AT BREAK	MD/TD	%	ASTM D-882	1000/1100
HAZE	-	%	ASTM D-1003	1
GLOSS(45°)	-	%°	ASTM D-2457	30

*All above mentioned data are typical values and not to be construed as real specifications.Users should confirm results by their own tests.For more information about guaranteed items, please refer to S.S.S.(Standard Sales Specifications)

**38µm film,2.5:1 blow up ratio,225°c melt temperature , MD: Machine Direction,TD:Transverse Direction

Grade Suffix(Additives Indication):

AA:GENERAL ANTIOXIDANT

	STANDARD SALES SPECIFICATIONS (GUARANTEED ITEMS)*	ISSUE DATE	Feb-15
	GRADE	WWW.TPCO.IR	
	LL0220AA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984114282612	

PROPERTY	UNIT	TEST METHOD	SPECIFICATION RANGE
MELT FLOW INDEX (2.16KG)	g/10min	ASTM D-1238	2-2.5
DENSITY	gr/cm3	ASTM D-1505	0.919-0.923
CONTAMINATION	NO.	BP137	≤4 DEFECTS IN 200GR OF PELLETS

*FOR MORE INFORMATION PLEASE CALL QUALITY ASSURANCE DEPARTMENT AT ABOVE ADDRESS