

DATA SHEET

GHAED BASSIR
PETROCHEMICAL CO.



ABS-HU-650

Classification: General ABS>Heat Resistance grade

Characteristic: Ultra Heat Resistance& High impact strength

Application: Mirror housings, Hair dryer shells, Electric oven exterior parts, Automobile parts and etc.

Property	Test method (ASTM)	Test condition	Unit	Typical value	ABS-HU 650 specification
Izod impact	D-256	6.4 mm , notched	Kj/m ²	18	Min16
Melt flow index	D-1238	220°C , 10 kg	gr/10 min	4.0	1-4
Rock well hardness	D-785	R-scale	110	100-120
HDT	D-648	1.82 m pa	°c	105	Min105
Vicat softening Temp	D-1525	5kg/50°C	°c	128	Min128
Tensile strength	D-638	23°C , 50 mm/min	Kg/cm ²	470	Min 440
Tensile elongation	D-638	23°C , 50 mm/min	%	22	Min 16
Flexural strength	D-790	23°C , 2.8 mm/min	Kg/cm ²	700	Min 670
Flexural Modulus	D-790	23°C , 2.8 mm/min	Kg/cm ²	22000	Min 20000
Specific Gravity	D-792	23°C	..	1.04	1.04
Molding Shrinkage	D-955	...	%	0.4-0.7	0.4-0.7
Flammability	UI94	1/8inch(3.2mm)	...	HB	HB

TYPICAL ABS PROCESSING CONDITIONS

DRYING: it is recommended that GBPC ABS Heat Resistance Resins be dried at (80-90°C)for 3 hours. A moisture level of ≤0.1% should be reached before injection molding the resin.

The following molding conditions are recommended starting point for GBPC ABS Resin.Some modifications may be required depending on the specific molding equipment and part configuration.

INJECTION MOLDIN

Rear Temp(°c)	Center Temp (°c)	Center Temp (°c)	Front Temp (°c)	Nozzle Temp (°c)	Melt Temp (°c)
200-210	210-220	210-220	220-230	220-240	250
Mold Temp (°c)	Filling Speed				
60-70	Slow-Med				