## **Product Data and Technical Information**

POLYMER TYPE: POLYPROPYLENE HOMOPOLYMER

GRADE NAME: RG 1125 MC

PACKING: PP bags of 25 kgs, 50 bags on a pallet shrinked by PE

APPLICATION: Cast films (medium slip) for all kind of packaging e.g. Flower & food

**PRODUCT FEATURES**: Homopolymer with good optical properties and high stiffness

PROCESSING METHOD: Extrusion

Property	Test Method	Unit	Value
MFR ( 230° C/ 2.16 Kg )	ASTM D1238/L	gr/10min	8.5
Tear strength(Longitudinal/Transverse)	DIN 53455	MPa	40/36
Elongation at break(Longitu./Trans.)	DIN 53455	%	660/680
Flexural modulus (Longitu./Trans.)	DIN 53121	Мра	650/630
Dart drop impact strength F50	ASTM D1709	gr	330
Coefficient of sliding friction	DIN 53375	-	0.25
Melting Point , DSC	ASTM D3417	°C	163
Gloss( 20°)	ISO 2813	%	120
Haze	ASTM D1003	%	1.8
Density	ASTM D792	gr/cm3	0.91

The information in this publication is submitted without prejudice, and is based on our current "" " .knowledge and experience and on a limited number of tests

In view of the many factors that may affect processing and application, these data do not relieve the receiver of this information from the responsibility of carrying out their own tests and experiments; neither do they imply and legally binding assurance of certain properties or of suitability for a specific purpose of the products made with or on the basis of the information in this publication



Tel: +98(311)6305851-5 Fax: +98(311)6305856 eMail: info@Regalpetro.com