

HDPE made via Hostalen Process



Product data sheet
HC7260*

For transport and stacking crates, particularly bottle crates.

HDPE: HC7260*

Density: 0.960

MFI: 23±3

Features



- Low war page
- good impact strength
- good stress uracil resistance

Applications



- Injection moulding

Additives



- Antioxidant/Process stabilizer
- Lubricant (processing aid)/ acid scavenger

Material properties (This data are typical values and are not to be construed as product specifications.)

Test/Composition	Typical Value	Unit	Method
Density	0.960	g/cm ³	ISO 1183
MFR190°/2.16	8	g/10min	ISO1133
MFR190°/5	23	g/10min	ISO1133
Notched Impact (23°C)	≥4	mJ/mm ²	ISO179/1eA

- Test specimen from compression moulded sheet at 23°C.
- FRR values are statistical and calculated by dividing MFR values.
- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted are average values .