



HDPE made via Hostalen Process



## Product data sheet HF4750K

HDPE: HF4750K

Density: 0.946

MFI: 3.5

Features



----

Applications



- Cable Insulation

Additives



- Antioxidant/Process stabilizer
- Lubricant (processing aid)/ acid scavenger

**Material properties** (This data are typical values and are not to be construed as product specifications.)

122

Test/Composition	Typical Value	Unit	Method
Density	0.946	g/cm <sup>3</sup>	ISO 1183
FRR 21.6/5	20		
MFR 190° /21.6	70	g/10min	ISO1133
MFR190° /5	3.5	g/10min	ISO1133

- Test specimen from compression moulded sheet at 23°C.
- FRR values are statistical and calculated by dividing MFR values.
- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted are average values .