



HDPE made via Hostalen Process



Product data sheet HF7740F

- Stretched film and tapes for production of high-strength knitted and wover.

HDPE: HF7740F

Density: 0.944

MFI: 1.8

Features



- Butene copolymer
- Excellent mechanical properties
- Excellent puncture resistance
- High impact strength

Applications



- Stretched tape (raffia)

Additives



- Antioxidant / Process stabilizer
- Lubricant (processing aid) / acid scavenger

Material properties (This data are typical values and are not to be construed as product specifications.)

118

Test/Composition	Typical Value	Unit	Method
Density	0.944	g/cm ³	ISO 1183
Fish Eye Note	≤ 4	note	internal
FRR 21.6/5	15		
MFR 190° /21.6	27	g/10min	ISO1133
MFR190° /5	1.8	g/10min	ISO1133

- Test specimen from compression moulded sheet at 23°C.

- FRR values are statistical and calculated by dividing MFR values.

- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted are average values .