Globally Distinguished

Product data sheet - Tapes tobe used for agricultural	l packing and as protective cover
	pucking and as protective cover.
HF7740F2	

HDPE: HF7740F2	Density: 0.944	MFI: 1.8±0.3
Features O	Applications	Additives
• <i>Medium melecular low-density</i> grade with a narrow molar mass distribution	• Stretched tape (raffia)	<ul> <li>Antioxidant/Process stabilizer</li> <li>Lubricant (processing aid)/ acid scavenger</li> </ul>

*Material properties* (This data are typical values and are not to be construed as product specifications.)

Test/Composition	Typical Value	Unit	Method
Density	0.944	g/cm <sup>3</sup>	ISO 1183
Fish Eye Note	≤4	Note	internal
FRR 21.6/5	12		
MFR 190°/21.6	21	g/10min	ISO1133
MFR190°/5	1.8	g/10min	ISO1133
Notched Impact (23°c)	15	mJ/mm <sup>2</sup>	ISO179/1eA

- Test specimen from compression moulded sheet at 23°C.

- FRR values are statistical and calculated by dividing MFR values.

- Notch Impact Test specimen from compressed moulded sheet  $23\,^\circ$ C and The data quoted are average values .