

HDPE made via Hostalen Process



Product data sheet  
**HF7750M2**

**HDPE: HF7750M2**

**Density: 0.956**

**MFI: 3.3**

Features



- Medium molecular high density grade with a narrow molar mass distribution

Applications



- Monofilament

Additives



- Antioxidant / Process stabilizer
- Lubricant (processing aid) / acid scavenger

**Material properties** (This data are typical values and are not to be construed as product specifications.)

Test/Composition	Typical Value	Unit	Method
Density	0.956	g/cm <sup>3</sup>	ISO 1183
FRR 21.6/5	10		
MFR 190° /21.6	33	g/10min	ISO1133
MFR190° /5	3.3	g/10min	ISO1133
Notched Impact (23° c)	25	mJ/mm <sup>2</sup>	ISO179/1eA

- Test specimen from compression moulded sheet at 23°C.
- FRR values are statistical and calculated by dividing MFR values.
- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted are average values .