



HDPE made via Hostalen Process



Product data sheet HH4765

HDPE: HH4765

Density: 0.959

MFI: 1.5±0.3

Features



- Butene copolym
- Excellent mechanical properties
- Excellent puncture resistance
- High impact strength

Applications



- Small blow moulding

Additives



- Antioxidant / Process stabilizer
- Lubricant (processing aid) / acid scavenger

Material properties (This data are typical values and are not to be construed as product specifications.)

116

Test/Composition	Typical Value	Unit	Method
Density	0.959	g/cm ³	ISO 1183
FRR 21.6 /5	18		
MFR 190° /21.6	27	g/10min	ISO1133
MFR190° /5	1.5	g/10min	ISO1133
Notched Impact (23° c)	7	mJ/mm ²	ISO179/1eA

- Test specimen from compression moulded sheet at 23°C.

- FRR values are statistical and calculated by dividing MFR values.

- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted are average values .