

LLDPE made via Spherilene Process



Product data sheet
20505

-20505 is the general purpose injection molding grade.

LLDPE: (butene) Injection Moulding

Density: 0.922

MFI: 5

Features



- Injection molding

Applications



- General Purpose

Additives



- THERMAL ANOTIOXIDANT
- ANTIBLOCKING AGENT
- SLIP AGENT

Material properties (This data are typical values and are not to be construed as product specifications.)

Test/Composition	Typical values	Unit	Method
Density	922	g/l	D 1505
Flexural Modulus	470	MPa	D 790
Izod 23°C	NB	J/m	D 256/A
MFR "E"	5	g/10 min	D 1238
Yield Strength	12.3	MPa	D 638

- Properties on compression moulded specimen according to method MA 17102, unless specified.