

## BAL 105 WS-70

### Long oil Alkyd Resin

Based on Soybean Oil Fatty Acid 70% in white spirit

#### Product Description:

BAL 105 WS-70 is a long oil alkyd resin based on soybean oil fatty acid which offers very good solvent tolerance and outstanding filler binding power.

#### Characteristics and Advantages:

- Very good solvent tolerance
- Outstanding filler binding power

#### Uses:

- Architectural paints and coatings
- Primer and surface
- Anti corrosion primers

#### Technical Properties:

##### Physical data in liquid state at 25°C

These data are measured for each lot by our QC lab before its release.

Properties	Unit	Value	Test method
Oil content (approx.)	wt%	50	Calculation
Color	Gardner	NA	ASTM D1544
Viscosity (at 25°C)	St	1000-1500	ASTM D1545
Acid number	mg KOH/g	Max 10	ASTM D1639
Solid content	wt%	69±1	ASTM D1259

##### Typical Properties

These data are not subject to routine monitoring or part of the specifications; they are only reported for a better product description.

Properties	Unit	Value	Test method
Density (at 23°C)	g/cm <sup>3</sup>	0.9998	ASTM D1475
Flash point (open cup)	°C	26	ASTM D92

##### Dilutability (Internal test method)

White Spirit	•	Butyl Acetate	•
Xylene	•	Acetone	•
Toluene	•	Butanol	○
Ethyl Acetate	•		

● = unlimited dilutability  
 ○ = substantial dilutability

⊙ = limited dilutability  
 ○ = very limited or no dilutability

##### Compatibility (ASTM D688 @T=160°C)

Aliphatic Polyisocyanate	Incompatible	Long Oil Alkyds	Incompatible
Medium Oil Alkyds	Compatible	Amino Resin	Incompatible
Short Oil Alkyds	Compatible	Hydroxyl Acrylic Resin	Incompatible

**Product safety and Environmental protection:**

The usual protective measures employed during the handling of Alkyd Resins should be observed. Further product safety information can be obtained from our Material Safety Data Sheet which is available on request.

**Packaging:** 190 kg (net) in steel drums.

**Storage:** Store in a cool place below 25 °C and away from moisture and direct sunlight.

**Disclaimer:** The information and in particular the recommendations relating to the application and use of Bonyan Kala Chemie products are given in good faith based on our current knowledge and expertise of the products when properly stored, handled and used under normal conditions within their shelf life. In practice, the differences in materials, chemistries and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request or can be accessed from [www.bonyankala.com](http://www.bonyankala.com).