

Rewopol SB DO 70

anionic substrate wetting additive

Special features

- for waterborne formulations
- highly effective
- improves wetting of various substrates and pigments
- excellent reduction of static and dynamic surface tension
- silicone-free

Storage stability

When stored in an original unopened packaging between +4 and +40 °C, the product has a shelf life of at least 24 months from the date of manufacture.

Recommended addition level

- architectural coatings
- industrial coatings
- recommended addition level as substrate wetting additive 0.5 - 3.0 % as supplied on total formulation, as dispersing additive 5 - 15 % as supplied calculated on pigment

Solubility

mixing ratio parts by weight	1 : 100	1 : 4
water	o	-
ethanol	o	-
isopropanol	+	o
butyl glycol	+	o
dipropyleneglycol monomethylether	+	o
n-ethyl-2-pyrrolidone	+	o
Texanol	+	-
mineral spirit	+	+

+ = clear, soluble, o = opalescent, - = cloudy, insoluble

Processing instructions

Addition as supplied is recommended.

Chemical description

solution of a sodium diisooctyl sulfosuccinate

Technical information

- delivery form liquid
- appearance clear liquid
- active matter content approx. 70 %
- solvent water / isopropanol 11 : 4

Registration status

REWOPOL® SB DO 70 respectively its ingredients are listed in the following chemical inventories: AICS, DSL, ECL, EINECS, ENCS, IECSC, PICCS, TSCA.

All intentional ingredients are listed on the DSL (Domestic Substance List) inventory or have been notified pursuant to the NSN (New Substances Notification) regulations.

All intentional ingredients are listed on the TSCA inventory or comply with the TSCA Polymer Exemption criteria according 40 CFR 723.

All intentional ingredients are listed on the ECL inventory or comply with the Polymer Exemption criteria.

All intentional ingredients are listed on the PICCS inventory or comply with the Polymer Exemption criteria.

Packaging

plastic L-ring drum 200 kg

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.
(Status: 11/2015)