

SILIKOFTAL® HTL 88

silicone polyester resin

Special features

- excellent dishwasher detergent resistance
- low thermoplasticity
- good adhesion
- without addition of organotin-containing compounds

Technical information

delivery form	liquid
appearance	clear to slightly hazy liquid (product properties are not affected by haziness)
non-volatile content	approx. 60 %
solvent	xylene / methoxypropylacetate 1 : 2
viscosity at 25 °C	approx. 3000 mPa s

Application

- non-stick coatings in combination with PTFE
- decorative coatings for cookware, household appliances and electric and gas heaters with a permanent thermal stability of 180 °C

Processing instructions

- All heat-resistant pigments can be used due to the product's excellent pigment compatibility.
- Limited miscibility with aromatic hydrocarbons.
- Application by spray (incl. electrostatic), dipping or brushing.

Dilution

Dilutable by esters, ketones and glycol ethers.

Baking conditions

280 °C/15 min.

Registration status

SILIKOFTAL® HTL 88 respectively its ingredients are listed in the following chemical inventories: ECL, EINECS, IECSC, PICCS.

All intentional ingredients are listed on the ECL inventory or comply with the Polymer Exemption criteria.

All intentional ingredients are listed on the PICCS inventory or comply with the Polymer Exemption criteria.

Packaging

steel drum with bung 200 kg

Storage stability

When stored in an original unopened packaging between +4 and +40 °C, the product has a shelf life of at least 12 months from the date of manufacture.

However, contact with tin (e.g. with metal containers) will shorten storage stability.

Keep dry. Contact with moisture causes gelation.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.
(Status: 11/2015)