

TEGO® Dispers 653

pigment-wetting and dispersing additive

Effects

	0	1	2	3	4	5
Viscosity reduction with organic pigments/carbon blacks						
Color intensity/gloss with organic pigments/carbon blacks						
Viscosity reduction with inorganic pigments/fillers						
Color intensity/gloss with inorganic pigments/fillers						

0 = unsuitable...5 = highly suitable

Special features

For the manufacture of universal colorants. For inorganic and organic pigments. Very good reduction of viscosity. Also for architectural paints. Solvent- and APE-free.

Suitability for

waterborne	solventborne
●	○
2-pack 100 %	radiation-curing
○	○
direct grind	resin-based pigment concentrates
○	●
resin-free pigment concentrates	universal pastes
●	●

● = suitable ... ○ = not suitable

Solubility in

water	ethanol
●	○
TPGDA	butyl acetate
●	○
white spirit	
○	

● = clear soluble, ● = cloudy but stable, ○ = insoluble

Recommended addition level

As supplied calculated on inorganic pigment: 12 - 25 %

As supplied calculated on organic pigment: 40 - 70 %

As supplied calculated on carbon black: 40 - 90 %

Processing instructions

Add to the grind before dispersion.

Formulation advices

- Alternative for higher color strength with organic pigments: TEGO® Dispers 650
- Combination partner for stronger reduction in viscosity with inorganic pigments: TEGO® Dispers 652
- In case of strong foam development, addition of TEGO® Foamex 8050 is recommended.
- For inorganic pigment concentrates the addition of rheology modifiers (for example fumed silica) has proven to be beneficial.
- For the production of carbon black concentrates often the addition of a small amount of amine (0.2 - 3.0%) to neutralize the partially acidic pigment surface is beneficial.
- Starting point formulations for the production of pigment concentrates are available upon request.

Chemical description

modified polyether with groups of high pigment affinity

Technical information

- appearance: clear liquid
- active matter content: approx. 35 %
- solvent: water

Registration status

TEGO® Dispers 653 respectively its ingredients are listed in the following chemical inventories: ECL, EINECS, NDSL, PICCS, TSCA, TCSI.

All intentional ingredients are listed on the TSCA inventory or comply with the TSCA Polymer Exemption criteria according 40 CFR 723.

Further information on regulatory topics can be found on the Regulatory Data Sheet.

All intentional ingredients are listed on the ECL inventory or comply with the Polymer Exemption criteria.

All intentional ingredients are listed on the PICCS inventory or comply with the Polymer Exemption criteria.

Packaging

- plastic pail 25 kg
- container 1000 kg

Storage stability

When stored in an original unopened packaging between +4 and +40 °C, the product has a shelf life of at least 24 months from the date of manufacture.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.
(Status: 11/2015)