



F 30 G

F 30 G is a medium-high fluidity polypropylene homopolymer for injection moulding.

Because of its good flow properties, this grade offers easy mould filling and short cycle times.

Articles produced from F30 G exhibit good dimensional stability and high stiffness.

F 30 G is widely used for injection moulding consumer goods such as food containers, cool boxes, vacuum flasks, flower pots, toys, garden furniture and small appliances.

In the medical sector, F 30 G is used for 3-part syringes and a wide range of health-care items.

Other applications are closures, caps and crates for products.



PROPERTIES	METHOD (b)	UNIT	TYPICAL VALUE (a)
Physical properties			
Melt flow rate (230°C, 2.16 kg)	ISO 1133	dg / min	12
Density	ISO 1183	g/cm ³	0.9
Mechanical properties			
Flexural modulus	ISO 178	N/mm ²	1550
Tensile strength yield	ISO R 527	N/mm ²	35
Elongation at yield	ISO R 527	%	13
Izod impact strength (notched) at 23°C	ISO 180	kJ/m ²	3.5
Hardness Shore D	ISO 868	points	71
Thermal properties			
Vicat softening point (9.8 N)	ISO 306/A	°C	155
H.D.T. (0.46 Mpa)	ISO 75/B	°C	117
Accelerated oven ageing in air (forced circulation) at 150°C	ISO 4577	hour	360

● F 30 G is suitable for food contact.

a) Values shown are averages and are not to be considered as product specification. These values may shift slightly as additional data are accumulated.

b) ISO test methods are the latest under the society's current procedures.

All specimens are prepared by injection moulding.