

## PVC-S6558

### 1) Product Description:

PVC contains approximately 56% by weight of chlorine. This polymer possesses thermoplastic properties. Grade S6558 has low porosity & high bulk density.

### 2) Applications:

- Pipe and fitting
- Injection moulding

### 3) Typical Data

Property	Unit	Value	Test Method
K-value	-	65	DIN- 53726
Sulphate ash	wt % max	0.05	DIN-53568/2
Volatiles	wt % max	0.2	ISO R-1269
Bulk density	gr/lit	600	DIN-53466
Screen analysis (residue on sieve)			
> 63 micron			DIN-53734
>250 micron	wt % min wt % max	90 5	DIN-53734
Dark resin (particles in 250gr PVC)	No.max	30	HULS-6.7
Plasticizer acceptance	grDOP/100grPVC min.	10	DIN-53417/1
Fish eyes	number per 25 cm2 max.	5	HULS-6.9
Flowability (dia. of funnel outlet)	mm max.	4	HULS-6.10
Viscosity number	Cm3/gr	105	DIN- 53726
Residual VCM	ppm	≤ 1	HULS-6.11

\* Typical Values : not to be construed as specifications

Producer: Bandar Imam Petrochemical Co.

Licensor: HULS

Packing: 25 Kg plastic bag