

TEGO® Phobe 6200

masonry water repellent for the formulation of solventborne impregnations and primers for mineral substrates

Area of application

	0	1	2	3	4	5
Fresh concrete	████████████████████					
Concrete	████████████████████					
Red brick	████████████████████					
Natural stone	████████████████████					
Stucco	████████████████████					

0 = unsuitable...5 = highly suitable

Special features

- excellent resistance to driving rain
- prevents salt blooming and efflorescence
- good penetration properties
- good coating adhesion

Recommended addition level

- solventborne impregnations and primers for alkaline and neutral substrates

Solubility

mixing ratio parts by weight	1 : 100	1 : 4
water	-	-
n-butanol	+	+
acetone	+	+
methylethylketone	+	+
butyl acetate	+	+
methoxypropylacetate	+	+
xylene	+	+
mineral spirit	+	+

+ = clear, soluble, o = opalescent, - = cloudy, insoluble

Processing instructions

- Flood-coating, spray, roller and brush-application is possible.
- The substrate must be dry, free from dust and clean.
- Please check the penetration properties of the substrate before application.

Dilution

- Addition of aliphatic and aromatic hydrocarbon solvents, as well as isoparaffins. The solvent should have a boiling range from 130 °C - 200 °C and an evaporation point of > 90°C. Water-free alcohols are also suitable for thinning.
- For impregnation a dilution of 5 - 25 % on solid content is necessary, depending on the absorbency.
- For producing solventborne primers, a combination with methacrylics is recommended (e. g. PLEXISOL® P 550/Kremer Pigmente GmbH & Co KG oder PLIOLITE® VTAC/ Eliokem). The preferred ratio of binder/solvent /TEGO® Phobe is 13/82/5.

Chemical description

low molecular weight modified polysiloxane resin

Technical information

- appearance clear liquid
- active matter content 100 %

Registration status

TEGO® Phobe 6200 respectively its ingredients are listed in the following chemical inventories: AICS, DSL, ECL, EINECS, ENCS, IECSC, PICCS, TSCA, NZIOC.

All intentional ingredients are listed on the DSL (Domestic Substance List) inventory or have been notified pursuant to the NSN (New Substances Notification) regulations.

All intentional ingredients are listed on the TSCA inventory or comply with the TSCA Polymer Exemption criteria according 40 CFR 723.

All intentional ingredients are listed on the ECL inventory or comply with the Polymer Exemption criteria.

All intentional ingredients are listed on the PICCS inventory or comply with the Polymer Exemption criteria.

Packaging

steel can 50 kg

Storage stability

12 months in unopened containers.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. (Status: 11/2015)