

Evonik Corporation Vestyron® 214 Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Heat Resistant Grade

Material Notes:

Uses: Packaging, household articles.ISO data as provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-Vestyron-214-Polystyrene.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	
Water Absorption	0.00 %	0.00 %	
Melt Flow	9.0 g/10 min	9.0 g/10 min	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	50.0 MPa	7250 psi	
Elongation at Break	2.0 %	2.0 %	
Modulus of Elasticity	3.20 GPa	464 ksi	
Charpy Impact Unnotched	1.00 J/cm ²	4.76 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
CTE, linear	<= 50.0 µm/m-°C	<= 27.8 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	85.0 °C	185 °F	
Deflection Temperature at 1.8 MPa (264 psi)	78.0 °C	172 °F	
Vicat Softening Point	88.0 °C	190 °F	50°C/hr/50 N
Glass Transition Temp, Tg	89.0 °C	192 °F	10°C/min (50°F/min)
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Flammability, UL94	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Oxygen Index	18 %	18 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	$\geq 1.00 \times 10^{15}$ ohm-cm	$\geq 1.00 \times 10^{15}$ ohm-cm	
Surface Resistance	1.00×10^{14} ohm	1.00×10^{14} ohm	
Dielectric Constant	2.0	2.0	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	2.0	2.0	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	65.0 kV/mm	1650 kV/in	
Dissipation Factor	0.00020	0.00020	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dissipation Factor	0.00020	0.00020	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	350 V	350 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China