

## Evonik Corporation Vestyron® 114 Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Heat Resistant Grade

**Material Notes:**

Uses: Packaging, industrial parts.ISO data as provided by the manufacturer.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Evonik-Corporation-Vestyron-114-Polystyrene.php](http://www.lookpolymers.com/polymer_Evonik-Corporation-Vestyron-114-Polystyrene.php)

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in <sup>3</sup>	
Water Absorption	0.00 %	0.00 %	
Melt Flow	2.0 g/10 min	2.0 g/10 min	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	60.0 MPa	8700 psi	
Elongation at Break	3.0 %	3.0 %	
Modulus of Elasticity	3.30 GPa	479 ksi	
Charpy Impact Unnotched	1.20 J/cm <sup>2</sup>	5.71 ft-lb/in <sup>2</sup>	

Thermal Properties	Metric	English	Comments
CTE, linear	<= 50.0 µm/m-°C	<= 27.8 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	100 °C	212 °F	
Deflection Temperature at 1.8 MPa (264 psi)	89.0 °C	192 °F	
Vicat Softening Point	102 °C	216 °F	50°C/hr/50 N
Glass Transition Temp, Tg	104 °C	219 °F	10°C/min (50°F/min)
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Flammability, UL94	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Oxygen Index	18 %	18 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	$\geq 1.00 \times 10^{15}$ ohm-cm	$\geq 1.00 \times 10^{15}$ ohm-cm	
Surface Resistance	$1.00 \times 10^{14}$ ohm	$1.00 \times 10^{14}$ ohm	
Dielectric Constant	2.0	2.0	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	2.0	2.0	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	65.0 kV/mm	1650 kV/in	
Dissipation Factor	0.00020	0.00020	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dissipation Factor	0.00020	0.00020	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	350 V	350 V	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China