

Evonik Corporation Vestyron® 527 S Impact-Modified Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Flame Retardant

Material Notes:

Uses: Housings, cases and peripherals for electronics.ISO data as provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-Vestyron-527-S-Impact-Modified-Polystyrene.php

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in ³	
Water Absorption	0.00 %	0.00 %	
Melt Flow	17 g/10 min	17 g/10 min	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	34.0 MPa	4930 psi	
Elongation at Break	30 %	30 %	
Elongation at Yield	1.0 %	1.0 %	
Modulus of Elasticity	2.75 GPa	399 ksi	
Charpy Impact Unnotched	5.00 J/cm ²	23.8 ft-lb/in ²	
	4.00 J/cm ²	19.0 ft-lb/in ²	@Temperature -30.0 °C @Temperature -22.0 °F
Charpy Impact, Notched	0.400 J/cm ²	1.90 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
CTE, linear	<= 50.0 µm/m-°C	<= 27.8 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	82.0 °C	180 °F	
Deflection Temperature at 1.8 MPa (264 psi)	77.0 °C	171 °F	
Vicat Softening Point	86.0 °C	187 °F	50°C/hr/50 N
Flammability, UL94	V-2	V-2	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-2	V-2	

Thermal Properties	Metric @ Thickness 3.20 mm	English @ Thickness 0.126 in	Comments
Oxygen Index	26 %	26 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	$\geq 1.00 \times 10^{15}$ ohm-cm	$\geq 1.00 \times 10^{15}$ ohm-cm	
Surface Resistance	1.00×10^{14} ohm	1.00×10^{14} ohm	
Dielectric Constant	2.0	2.0	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Constant	2.0	2.0	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	35.0 kV/mm	889 kV/in	
Dissipation Factor	0.00060	0.00060	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dissipation Factor	0.00060	0.00060	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	300 V	300 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China