

Evonik Corporation Vestamid® L2123 sw 9.7507 (as-conditioned) Nylon 12

Category : Polymer , Thermoplastic , Nylon , Nylon 12 , Nylon 12, Extrusion/Tubing Grade

Material Notes:

Uses: Flexible tubing for the automobile industry.ISO data as provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-Vestamid-L2123-sw-97507-as-conditioned-Nylon-12.php

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in ³	
Moisture Absorption at Equilibrium	<= 0.50 %	<= 0.50 %	Humidity Absorption

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	25.0 MPa	3630 psi	
Elongation at Break	>= 50 %	>= 50 %	
Elongation at Yield	30 %	30 %	
Modulus of Elasticity	0.400 GPa	58.0 ksi	
Charpy Impact Unnotched	NB	NB	
	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	NB	NB	
	0.800 J/cm ²	3.81 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	<= 50.0 µm/m-°C	<= 27.8 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	90.0 °C	194 °F	
Deflection Temperature at 1.8 MPa (264 psi)	45.0 °C	113 °F	
Vicat Softening Point	120 °C	248 °F	50°C/hr/50 N

Electrical Properties	Metric	English	Comments
Electrical Resistivity	7.00e+10 ohm-cm	7.00e+10 ohm-cm	

Electrical Properties	Metric	English	Comments
Surface Resistance	2.00e+12 ohm	2.00e+12 ohm	
Dielectric Constant	4.0	4.0	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	15	15	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	33.0 kV/mm	838 kV/in	
Dissipation Factor	0.14	0.14	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	0.33	0.33	
	@Frequency 100 Hz	@Frequency 100 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China