

Evonik Corporation Vestodur® GF 10 10% Glass Reinforced PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 10% Glass Fiber Filled

Material Notes:

Description: Degussa AG's High Performance Polymers Business Unit manufactures a range of polybutylene terephthalate compounds that are supplied under the registered trademark VESTODUR® . Material properties characterizing VESTODUR compounds are: high thermostability, high stiffness, low water absorption resulting in high dimensional stability, high hardness, good strength, good sliding friction behavior, low abrasion, good creep behavior, good electrical properties, good chemical resistance, good weathering resistance, good processability, no tendency to form stress cracks. Specific Notes for this Material: Glass-bead filled and glass-fiber reinforced compounds with elevated or high rigidity, partially low-warpage; e.g., for housing parts in the automotive industry. Information provided by degussa.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-Vestodur-GF-10-10-Glass-Reinforced-PBT.php

Physical Properties	Metric	English	Comments
Density	1.38 g/cc	0.0499 lb/in ³	ISO 1183
Water Absorption at Saturation	0.45 %	0.45 %	ISO 62
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	Pigmentation can change mold shrinkage.
Linear Mold Shrinkage, Transverse	0.016 cm/cm	0.016 in/in	Pigmentation can change mold shrinkage.
Melt Flow	31.74 g/10 min @Load 2.16 kg, Temperature 250 °C	31.74 g/10 min @Load 4.76 lb, Temperature 482 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	81	81	ISO 868
Ball Indentation Hardness	170 MPa	24700 psi	H30; ISO 2039-1
Tensile Strength, Yield	100 MPa	14500 psi	50 mm/min; ISO 527-1/2
Elongation at Break	4.2 %	4.2 %	50 mm/min; ISO 527-1/2
Elongation at Yield	3.7 %	3.7 %	50 mm/min; ISO 527-1/2
Tensile Modulus	4.70 GPa	682 ksi	ISO 527-1/2
Charpy Impact Unnotched	3.00 J/cm ² @Temperature -30.0 °C	14.3 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU
	3.00 J/cm ² @Temperature 23.0 °C	14.3 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU

Mechanical Properties	0.550 J/cm ² Metric	2.62 ft-lb/in ² English	Comments
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	0.600 J/cm ²	2.86 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	70.0 µm/m-°C	38.9 µin/in-°F	Longitudinal; ISO 11359
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
CTE, linear, Transverse to Flow	110 µm/m-°C	61.1 µin/in-°F	ISO 11359
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
Melting Point	221 - 226 °C	430 - 439 °F	DSC
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ISO 75-1/2
Deflection Temperature at 1.8 MPa (264 psi)	190 °C	374 °F	ISO 75-1/2
Vicat Softening Point	205 °C	401 °F	50N; ISO 306
	220 °C	428 °F	10N; ISO 306
Flammability, UL94	HB	HB	
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Oxygen Index	19 %	19 %	ISO 4589
Glow Wire Test	750 °C	1380 °F	IEC 60695-2-1/0-3
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Dielectric Constant	3.6	3.6	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	3.9	3.9	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	

Electrical Properties	Metric	English	Comments
Dielectric Strength	27.0 kV/mm	688 kV/in	K20/P50; IEC 60243-1
Dissipation Factor	0.0020	0.0020	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.019	0.019	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	300 V	300 V	Test Solution A, 100 drops; IEC 60112
	325 V	325 V	Test Solution A, CTI; IEC 60112

Descriptive Properties	Value	Comments
Electrolytic Corrosion	A1 Step	IEC 60426

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China