

## Evonik Corporation Vestamid® D16 Nylon 612 (Dry as Molded)

Category : Polymer , Thermoplastic , Nylon , Nylon 612 , Nylon 612, Unreinforced

### Material Notes:

Description: low-viscosity base product Applications: monofilaments, bristles with high recovery for paint brushes and tooth brushes Information provided by degussa.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Evonik-Corporation-Vestamid-D16-Nylon-612-Dry-as-Molded.php](http://www.lookpolymers.com/polymer_Evonik-Corporation-Vestamid-D16-Nylon-612-Dry-as-Molded.php)

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption at Equilibrium	1.0 %	1.0 %	23°C/50% R.H.; ISO 62
Water Absorption at Saturation	2.6 %	2.6 %	ISO 62
Linear Mold Shrinkage	0.014 cm/cm	0.014 in/in	127x12.7x3.2 mm (processing cond. acc. To ISO 1874-2)
Linear Mold Shrinkage, Transverse	0.010 cm/cm	0.010 in/in	127x12.7x3.2 mm (processing cond. acc. To ISO 1874-2)

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	58.0 MPa	8410 psi	ISO 527-2/1A
Elongation at Break	>= 50 %	>= 50 %	ISO 527-2/1A
Elongation at Yield	5.0 %	5.0 %	ISO 527-2/1A
Tensile Modulus	2.00 GPa	290 ksi	ISO 527-2/1A
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.500 J/cm <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.600 J/cm <sup>2</sup>	2.86 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	130 µm/m-°C	72.2 µin/in-°F	ISO 11359
	@Temperature 23.0 -	@Temperature 73.4 -	

Thermal Properties	55.0 °C Metric	131 °F English	Comments
Melting Point	215 °C	419 °F	Peak Temperature; ISO 3146, ISO 11357
Deflection Temperature at 0.46 MPa (66 psi)	150 °C	302 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	ISO 75
	75.0 °C	167 °F	When conditioned at 180°C for 1 hour; ISO 75
Vicat Softening Point	180 °C	356 °F	50N; ISO 306
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Dielectric Constant	3.2	3.2	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	3.8	3.8	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	28.0 kV/mm	711 kV/in	K20/P50; IEC 60243-1
Dissipation Factor	0.024	0.024	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.029	0.029	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	>= 600 V	>= 600 V	Test Solution A, 100 drops; IEC 60112

Descriptive Properties	Value	Comments
Electrolytic Corrosion	A1 Step	IEC 60426

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China