

Evonik Corporation Vestamid® L2140 sw 9.7504 (dry properties) Nylon 12

Category : Polymer , Thermoplastic , Nylon , Nylon 12 , Nylon 12 , Extrusion/Tubing Grade

Material Notes:

Uses: Tubing for the automobile industry according to DIN 73 378, Type: PA 12-HL.ISO data as provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-Vestamid-L2140-sw-97504-dry-properties-Nylon-12.php

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in ³	
Water Absorption	1.0 %	1.0 %	
Moisture Absorption at Equilibrium	<= 0.50 %	<= 0.50 %	Humidity Absorption
Melt Flow	30 g/10 min	30 g/10 min	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	48.0 MPa	6960 psi	
Elongation at Break	>= 50 %	>= 50 %	
Elongation at Yield	5.0 %	5.0 %	
Modulus of Elasticity	1.50 GPa	218 ksi	
Charpy Impact Unnotched	NB	NB	
	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.10 J/cm ²	5.24 ft-lb/in ²	
	0.700 J/cm ²	3.33 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	100 µm/m-°C	55.6 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	100 µm/m-°C	55.6 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	110 °C	230 °F	

Thermal Properties <small>Deflection Temperature at 1.8 MPa (104 psi)</small>	50.0 °C Metric	122 °F English	Comments
Vicat Softening Point	140 °C	284 °F	50°C/hr/50 N
UL RTI, Electrical	120 °C	248 °F	
UL RTI, Mechanical with Impact	85.0 °C	185 °F	
UL RTI, Mechanical without Impact	95.0 °C	203 °F	
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	2.00e+14 ohm-cm	2.00e+14 ohm-cm	
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	
Dielectric Constant	3.0	3.0	
	@Frequency 100 Hz	@Frequency 100 Hz	
	3.0	3.0	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	32.0 kV/mm	813 kV/in	
Dissipation Factor	0.030	0.030	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	0.040	0.040	
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China