

Evonik CYRO Paraglas Soundstop® Transparent Sheet

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, Optical Sheet

Material Notes:

Paraglas Soundstop is a standard clear transparent sheet Information provided by Cyro Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-CYRO-Paraglas-Soundstop-Transparent-Sheet.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	69.0 MPa	10000 psi	ASTM D638
Elongation at Break	4.5 %	4.5 %	ASTM D638
Tensile Modulus	2.80 GPa	406 ksi	ASTM D638
Flexural Strength	117 MPa	17000 psi	ASTM D790
Flexural Modulus	3.30 GPa	479 ksi	ASTM D790
Compressive Strength	117 MPa	17000 psi	ASTM D695
Charpy Impact Unnotched	1.365 J/cm ²	6.496 ft-lb/in ²	Weathered 5 years; ASTM D4812
	1.365 J/cm ²	6.496 ft-lb/in ²	At -5°F; ASTM D4812
	1.365 J/cm ²	6.496 ft-lb/in ²	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear	72.0 µm/m-°C	40.0 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Maximum Service Temperature, Air	>= 71.1 °C	>= 160 °F	
Deflection Temperature at 1.8 MPa (264 psi)	90.6 °C	195 °F	ASTM D648
Vicat Softening Point	105 °C	221 °F	ASTM D1525
Flame Spread	15 mm/min	0.60 in/min	ASTM D635
	@Thickness 15.0 mm	@Thickness 0.591 in	

Optical Properties	Metric	English	Comments
Refractive Index	1.49	1.49	ASTM D542

Optical Properties	Metric	English	Comments
	1.5 %	1.5 %	ASTM D1003 Weathered 5 years AZ; ASTM D1003
Yellow Index	<= 1.0 %	<= 1.0 %	ASTM E 313
	1.5 %	1.5 %	Weathered 5 years AZ; ASTM E 313
Transmission, Visible	92 %	92 %	Weathered 5 years AZ
	92 %	92 %	ASTM D1003

Descriptive Properties	Value	Comments
Resistance to Brushfire	Class2	15mm, EN1794-2
Resistance to stone projectiles	Pass	15mm, EN1794-1
Self Ignition Temperature °F	850	ASTM D1929
Smoke Density, % (15mm thick)	20	ASTM D2843
Sound Transmission Loss, dB (15mm)	32	ASTM E 90
Sound Transmission Loss, dB (20mm)	34	ASTM E 90
Sound Transmission Loss, dB (25mm)	36	ASTM E 90

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China