

Evonik Corporation Rohacell® 51 HF High Frequency Grade Polymethacrylimide (PMI) Foam

Category : Other Engineering Material , Composite Core Material , Polymer , Thermoset , Polymethacrylimide

Material Notes:

Description: ROHACELL® is produced by thermal expansion of a co-polymer sheet of methacrylic acid and methacrylonitrile. During the foaming process the copolymer sheet is converted to PMI - PolyMethacrylimide. Alcohol is used as a blowing agent, thus ROHACELL® contains no fluorinated carbon hydrates and is halogen free. It has a very homogeneous cell structure and isotropic properties. Specific Notes for this Material: ROHACELL® HF (= High Frequency) is a closed-cell rigid foam plastic based on PMI (polymethacrylimide) which does not contain any CFCs. The fields of application for ROHACELL® HF are antennas, radomes and X-ray tables. Curing temperature up to 130C (266F). Curing pressure up to 0.35 MPa (50 psi). Sandwich components using ROHACELL® HF as core material can be realized in a single work step (= cocuring). ROHACELL® HF is easy to shape. Thermoformability is another advantage of the core material. Information provided by degussa.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-Rohacell-51-HF-High-Frequency-Grade-Polymethacrylimide-PMI-Foam.php

Physical Properties	Metric	English	Comments
Density	0.0521 g/cc	0.00188 lb/in ³	DIN 53420, ISO 845, ASTM D 1622

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	1.90 MPa	276 psi	DIN 53455, ISO 527-2, ASTM D 638
Elongation at Break	4.0 %	4.0 %	DIN 53455, ISO 527-2, ASTM D 638
Modulus of Elasticity	0.0700 GPa	10.2 ksi	ISO 527-2, ASTM D 638
Compressive Strength	0.900 MPa	131 psi	DIN 53421, ISO 844, ASTM D 1621
Shear Modulus	0.0190 GPa	2.76 ksi	DIN 53294, ASTM C 273
Shear Strength	0.800 MPa	116 psi	DIN 53294, ASTM C 273

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 °C	356 °F	Heat Distortion Resistance; DIN 53424

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China