

## Evonik Corporation Rohacell® 51 IG Industrial Grade Polymethacrylimide (PMI) Foam

Category : Other Engineering Material , Composite Core Material , Polymer , Thermoset , Polymethacrylimide

### Material Notes:

Description: ROHACELL® is produced by thermal expansion of a co-polymer sheet of methacrylic acid and methacrylonitrile. During the foaming process the copolymer sheet is converted to PMI - PolyMethacrylimide. Alcohol is used as a blowing agent, thus ROHACELL® contains no fluorinated carbon hydrates and is halogen free. It has a very homogeneous cell structure and isotropic properties. Specific Notes for this Material: ROHACELL® IG (=Industrial Grade) is a closed-cell rigid foam plastic based on PMI (polymethacrylimide) which does not contain any CFCs. The fields of application for ROHACELL® IG are model building, vehicle construction and shipbuilding, as well as the manufacture of sports articles and X-ray tables. Information provided by degussa.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Evonik-Corporation-Rohacell-51-IG-Industrial-Grade-Polymethacrylimide-PMI-Foam.php](http://www.lookpolymers.com/polymer_Evonik-Corporation-Rohacell-51-IG-Industrial-Grade-Polymethacrylimide-PMI-Foam.php)

Physical Properties	Metric	English	Comments
Density	0.0521 g/cc	0.00188 lb/in <sup>3</sup>	DIN 53420, ISO 845, ASTM D 1622

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	1.90 MPa	276 psi	DIN 53455, ISO 527-2, ASTM D 638
Elongation at Break	4.0 %	4.0 %	DIN 53455, ISO 527-2, ASTM D 638
Modulus of Elasticity	0.0700 GPa	10.2 ksi	ISO 527-2, ASTM D 638
Flexural Strength	1.60 MPa	232 psi	DIN 53423, ISO 1209, ASTM D 790
Compressive Strength	0.900 MPa	131 psi	DIN 53421, ISO 844, ASTM D 1621
Shear Modulus	0.0190 GPa	2.76 ksi	DIN 53294, ASTM C 273
Shear Strength	0.800 MPa	116 psi	DIN 53294, ASTM C 273

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 °C	356 °F	Heat Distortion Resistance; DIN 53424

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China