

Evonik Corporation Rohacell® 71 IG Industrial Grade Polymethacrylimide (PMI) Foam

Category: Other Engineering Material, Composite Core Material, Polymer, Thermoset, Polymethacrylimide

Material Notes:

Description: ROHACELL® is produced by thermal expansion of a co-polymer sheet of methacrylic acid and methacrylonitrile. During the foaming process the copolymer sheet is converted to PMI - PolyMethacryllmide. Alcohol is used as a blowing agent, thus ROHACELL® contains no fluorinated carbon hydrates and is halogen free. It has a very homogeneous cell structure and isotropic properties. Specific Notes for this Material: ROHACELL® IG (=Industrial Grade) is a closed-cell rigid foam plastic based on PMI (polymethacrylimide) which does not contain any CFCs. The fields of application for ROHACELL® IG are model building, vehicle construction and shipbuilding, as well as the manufacture of sports articles and X-ray tables. Information provided by degussa.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-Rohacell-71-IG-Industrial-Grade-Polymethacrylimide-PMI-Foam.php

Physical Properties	Metric	English	Comments
Density	0.0750 g/cc	0.00271 lb/in ³	DIN 53420, ISO 845, ASTM D 1622

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	2.80 MPa	406 psi	DIN 53455, ISO 527-2, ASTM D 638
Elongation at Break	4.5 %	4.5 %	DIN 53455, ISO 527-2, ASTM D 638
Modulus of Elasticity	0.0920 GPa	13.3 ksi	ISO 527-2, ASTM D 638
Flexural Strength	2.50 MPa	363 psi	DIN 53423, ISO 1209, ASTM D 790
Compressive Strength	1.50 MPa	218 psi	DIN 53421, ISO 844, ASTM D 1621
Shear Modulus	0.0290 GPa	4.21 ksi	DIN 53294, ASTM C 273
Shear Strength	1.30 MPa	189 psi	DIN 53294, ASTM C 273

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 °C	356 °F	Heat Distortion Resistance; DIN 53424

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China