

## Evonik Corporation Rohacell® 110EC-5 Electrically Conductive Grade Polymethacrylimide (PMI) Foam

Category : Other Engineering Material , Composite Core Material , Polymer , Thermoset , Polymethacrylimide

### Material Notes:

Description: ROHACELL® is produced by thermal expansion of a co-polymer sheet of methacrylic acid and methacrylonitrile. During the foaming process the copolymer sheet is converted to PMI - PolyMethacrylimide. Alcohol is used as a blowing agent, thus ROHACELL® contains no fluorinated carbon hydrates and is halogen free. It has a very homogeneous cell structure and isotropic properties. Specific Notes for this Material: ROHACELL® EC (= Electrically Conductive) is a closed-cell rigid foam plastic based on PMI (polymethacrylimide) which does not contain any CFCs. ROHACELL® EC is a specially developed material for applications where electro conductivity is desirable. Any commonly used manufacturing technique, such as autoclave, press molding and resin infusion can be applied. Thermoformability is another advantage of ROHACELL® EC. Information provided by degussa.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Evonik-Corporation-Rohacell-110EC-5-Electrically-Conductive-Grade-Polymethacrylimide-PMI-Foam.php](http://www.lookpolymers.com/polymer_Evonik-Corporation-Rohacell-110EC-5-Electrically-Conductive-Grade-Polymethacrylimide-PMI-Foam.php)

Physical Properties	Metric	English	Comments
Density	0.110 g/cc	0.00398 lb/in <sup>3</sup>	DIN 53420, ISO 845, ASTM D 1622

Mechanical Properties	Metric	English	Comments
Compressive Strength	2.70 MPa	392 psi	DIN 53421, ISO 844, ASTM D 1621
Shear Strength	2.00 MPa	290 psi	DIN 53294, ASTM C 273

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	Heat Distortion Resistance; DIN 53424

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China