

## Evonik Corporation Solimide® AC-530-MMS-BMS Polyimide Foam

Category : Polymer , Thermoplastic , Polyimide, Thermoplastic

### Material Notes:

Description: SOLIMIDE® foams provide weight savings, improved handling/installation characteristics and enhanced durability compared to traditional insulation, resulting in lower operating and life cycle costs. In addition, the foams are extremely fire resistant and do not support combustion in normal atmospheres. Toxic gas, smoke generation and offgassing are virtually non-existent. These foam products are widely used in private, commercial, and military aircraft. SOLIMIDE® foams are specified and flying in Airbus, Boeing, Canadair, Boeing-Douglas, Hughes Helicopter, and Sikorsky Helicopter aircraft, among others. Meets BMS 8-300, MMS 04-001, and they are also approved for use in NASA systems. Information provided by degussa.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Evonik-Corporation-Solimide-AC-530-MMS-BMS-Polyimide-Foam.php](http://www.lookpolymers.com/polymer_Evonik-Corporation-Solimide-AC-530-MMS-BMS-Polyimide-Foam.php)

Physical Properties	Metric	English	Comments
Density	0.00545 g/cc	0.000197 lb/in <sup>3</sup>	ASTM D3574A

Mechanical Properties	Metric	English	Comments
Compressive Strength	0.00276 MPa	0.400 psi	Load Deflection at 25% Compression; Boeing BMS 8-300
Compression Set	<= 30 %	<= 30 %	50% Deflection; ASTM D3574D

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.0490 W/m-K	0.340 BTU-in/hr-ft <sup>2</sup> -°F	ASTM C518
Maximum Service Temperature, Air	200 °C	392 °F	Continuous Use
Flammability Test	0.00	0.00	seconds, Vertical Burn After Flame Time (Burn Length = 1.5 inches with no dripping); FAR 25.853(a), Appendix F, Part 1, (a)(1)(i)
Oxygen Index	30 %	30 %	ASTM D2863

Descriptive Properties	Value	Comments
Acoustical Absorption Coefficient (1000Hz)	0.99 sabins/m <sup>2</sup>	25 mm, ASTM C423 and E795, Type A Mounting
Acoustical Absorption Coefficient (125 Hz)	0.07 sabins/m <sup>2</sup>	25 mm, ASTM C423 and E795, Type A Mounting
Acoustical Absorption Coefficient (2000 Hz)	1.03 sabins/m <sup>2</sup>	25 mm, ASTM C423 and E795, Type A Mounting
Acoustical Absorption Coefficient (250 Hz)	0.18 sabins/m <sup>2</sup>	25 mm, ASTM C423 and E795, Type A Mounting
Acoustical Absorption Coefficient	0.86 sabins/m <sup>2</sup>	

(4000 Hz) Descriptive Properties	Value	25 mm, ASTM C423 and E795, Type A Mounting Comments
Acoustical Absorption Coefficient (500 Hz)	0.61 sabins/m <sup>2</sup>	25 mm, ASTM C423 and E795, Type A Mounting
Flexibility	No Creasing or Tearing	Boeing BMS 8-300
Noise Reduction Coefficient	0.7	25 mm, ASTM C423 and E795, Type A Mounting
Smoke Emission at 4 Minutes	3	FAR 25.853(d), Appendix F, Part V
Toxic Gas Generation	141 ppm CO	HCN, HF, HCl, NO <sub>x</sub> , or SO <sub>2</sub> not detected, Boeing BSS 7239, flaming mode

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China