



Solmer

SOLTECH LTD.

368-2, SANMAKDONG, YANGSAN,
KYOUNGNAM, 626-120, KOREA.

TEL : 82 55 387 6468
FAX : 82 55 387 6470
E-MAIL : th.choi@uvpia.com
URL : <http://www.uvpia.com>

Aliphatic Urethane Acrylate

SU 564

Descriptions

SU 564 is a trifunctional aliphatic urethane acrylate oligomer with 1,6-hexanediol diacrylate. This product is characterized good abrasion and stain resistance, fast cure and non-yellowing properties.

Features

- Good abrasion and stain resistance.
- Good flexibility and toughness.
- Fast curing.
- Light color.
- Non-yellowing.

Specifications

- Viscosity (mPa.s, 25°C)	37,500 ~ 52,500
- Color (Gardner)	2 Max
- Density (g/cm ³)	1.08
- Molecular weight	2,000
- Functionality	3
- Polymer solid % by weight	85
- HDDA % by weight	15

Applications

- Method : spray, screen, roll and curtain coating.
- Substrate : plastics, wood.
- Wood flooring and plastics coating.
- Overprint varnishes and screen inks.
- Clear coatings.
- Light stable coatings.

Handling

Storage :

Avoid continuous staying over than 40°C
Handle with care and avoid unnecessary personal contact.

Avoid contact with eyes and prolonged or repeated skin contact.

Avoid continuous or repetitive breathing of dust.