

Evonik Corporation Vestamelt® X1310 Copolyamide Development Hotmelt Adhesive

Category: Polymer, Adhesive, Thermoplastic, Nylon

Material Notes:

Description: High Performance Polymers manufactures a line of customized hotmelt adhesives. They are supplied as powders and granulates under the trade name VESTAMELT®. Used in a variety of industries, they provide all applications with a good balance of high-quality service properties, easy and reliable processing, and high cost-effectiveness. VESTAMELT® features the following special properties:economic bonding, also to sensitive textiles and surfaces that are difficult to fusehigh resistance to washing and dry cleaninggood resistance to strike back steam resistancesolvent resistance VESTAMELT® powders or granulates can be applied to substrates by means of typical processes. VESTAMELT® hotmelt adhesives are used in various application fields:In the textile industry they bond interlinings in women's and men's garments. In addition, they are successfully used in technical textile manufacturing. The automotive industry uses the thermoplastic hotmelt adhesives to fix interior trim and seat heaters on the one hand, on the other hand for the reliable bonding of paper to aluminum for the construction of fuel filters. Copolyamide hotmelt adhesives permit cost-effective manufacture of advanced components as windows, ceilings, carpets and acoustic insulation systems with lightweight panels. To make deflection yokes, insulated wires are coated with hotmelt varnishes and bonded together. The dimensionally stable coils obtained in this way find application in the electrical industry. Information provided by degussa.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-Vestamelt-X1310-Copolyamide-Development-Hotmelt-Adhesive.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	1.3	1.3	Solution Viscosity
	110 g/10 min	110 g/10 min	increase in molecular weight is
Melt Flow	@Load 2.16 kg, Temperature 160 °C	@Load 4.76 lb, Temperature 320 °F	possible above 150°C

Thermal Properties	Metric	English	Comments
Melting Point	110 °C	230 °F	Kofler Bar Tack Point
	110 °C	230 °F	DSC Melting Point
	117°C	243 °F	Optical Melting Point
	125 °C	257 °F	Kofler Bar Melting Point

Descriptive Properties	Value	Comments
Heat Setting Pressure	3-5 N/cm ²	
Heat Setting Temperature	120-150°C	crosslinking starts at 160°C, temperature action takes at least 30 s
Heat Setting Time	10-60 seconds	



Descriptive Properties	Very Good Value	Comments
Resistance to Steam	Very Good	
Resistance to Washing at 60°C	Very Good	
Supply Form	Powder	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China