

Evonik Corporation Vestamelt® X1338 Copolyamide Development Hotmelt Adhesive

Category : Polymer , Adhesive , Thermoplastic , Nylon

Material Notes:

Description: High Performance Polymers manufactures a line of customized hotmelt adhesives. They are supplied as powders and granulates under the trade name VESTAMELT®. Used in a variety of industries, they provide all applications with a good balance of high-quality service properties, easy and reliable processing, and high cost-effectiveness. VESTAMELT® features the following special properties: economic bonding, also to sensitive textiles and surfaces that are difficult to fuse, high resistance to washing and dry cleaning, good resistance to strike back steam, solvent resistance. VESTAMELT® powders or granulates can be applied to substrates by means of typical processes. VESTAMELT® hotmelt adhesives are used in various application fields: In the textile industry they bond interlinings in women's and men's garments. In addition, they are successfully used in technical textile manufacturing. The automotive industry uses the thermoplastic hotmelt adhesives to fix interior trim and seat heaters on the one hand, on the other hand for the reliable bonding of paper to aluminum for the construction of fuel filters. Copolyamide hotmelt adhesives permit cost-effective manufacture of advanced components as windows, ceilings, carpets and acoustic insulation systems with lightweight panels. To make deflection yokes, insulated wires are coated with hotmelt varnishes and bonded together. The dimensionally stable coils obtained in this way find application in the electrical industry. Information provided by degussa.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-Vestamelt-X1338-Copolyamide-Development-Hotmelt-Adhesive.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	1.4	1.4	Solution Viscosity
Melt Flow	45 g/10 min	45 g/10 min	
	@Load 2.16 kg, Temperature 160 °C	@Load 4.76 lb, Temperature 320 °F	

Thermal Properties	Metric	English	Comments
Melting Point	95.0 °C	203 °F	Kofler Bar Tack Point
	120 °C	248 °F	Optical Melting Point
	121 °C	250 °F	DSC Melting Point
	128 °C	262 °F	Kofler Bar Melting Point

Descriptive Properties	Value	Comments
Heat Setting Pressure	3-5 N/cm ²	
Heat Setting Temperature	115-150 °C	
Heat Setting Time	10-15 seconds	

Resistance to Dry Cleaning Descriptive Properties	Very Good Value	Comments
Resistance to Steam	Very Good	
Resistance to Washing at 60°C	Very Good	
Supply Form	Powder	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China