



## **Product Information**

## Bayferrox® 222 FM

## Description

| Туре  | Red pigment   |
|---|---|
| Delivery form   | Powder  |
| Chemical class<br>Colour Index<br>CAS-No.<br>REACH registration no. | Synthetic iron oxide α - Fe₂O₃<br>Pigment red 101 (77491)<br>1309-37-1<br>01-2119457614-35-0000 |

## **Specified Color Data**

| Colour values and tinting strength                                       |                  |     |                            |                       |                                      |
|--|------------------|-----|----------------------------|-----------------------|--------------------------------------|
| Standard   | Bayferrox 222 FM |     |                            |                       |                                      |
| Year   | 1997             |     |                            |                       |                                      |
| Binder:<br>Test paste based on a non drying<br>alkyd resin <sup>46</sup> | Full sha         | ade | Reduction with tital (1:5) | on ⁴⁵<br>nium dioxide | Test method<br>No. 001 <sup>41</sup> |
| $\Delta L^*$   | -0.5             | 0.5 |                            |                       |                                      |
| ∆ a*   | -1.0             | 1.0 | -1.2                       | 1.2                   |                                      |
| $\Delta b^*$   | -1.2             | 1.2 | -1.4                       | 1.4                   |                                      |
| $\Delta E^*_{ab}$  |                  | 1.5 |                            | 1.7                   |                                      |
| Relative tinting strength [%]  |                  |     | 95                         | 110                   |                                      |

## **Specified Technical Data**

| Dispersibility                               | min | max      | Test method                         |
|--|-----|----------|-------------------------------------|
| Binder Alkydal F 681<br>75 % in white spirit |     |          |                                     |
| Fineness of grind [µm]                       |     | 30/50/75 | No. 004 41                          |
| Technical Data                               | min | max      | Test method                         |
| Water-soluble content [%]                    |     | 0.5      | similar to<br>DIN EN ISO 787-3:2000 |
| Sieve residue (0.045 mm sieve) [%]           |     | 0.003    | DIN EN ISO 787-7:2009               |
| pH value                                     | 5   | 8        | DIN EN ISO 787-9:1995               |



# Bayferrox® 222 FM



### Informative Technical Data (guide values)

| a - Fe <sub>2</sub> O <sub>3</sub> content [%] <sup>53</sup> | > |     | 99.1           |     | <b>Test method</b><br>Information about the<br>determination of iron oxide <sup>41</sup> |
|--|---|-----|----------------|-----|--|
| Loss on ignition at 1000 °C, 0.5 h [%]                       | < |     | 1.0            |     | DIN 55913-2:1972   |
| Moisture content (after production) [%]                      | < |     | 0.5            |     | DIN EN ISO 787-2:1995  |
| Particle shape<br>Predominant particle size [µm]             | ~ |     | spherio<br>0.2 | al  | Electron micrographs<br>Electron micrographs   |
| Oil absorption [g/100 g]                                     | ~ |     | 15             |     | DIN EN ISO 787-5:1995  |
| Tamped density [g/ml]  |   | 1.4 | -              | 1.8 | similar to<br>DIN EN ISO 787-11:1995   |
| Density [g/ml]   | ~ |     | 5.0            |     | DIN EN ISO 787-10:1995   |

<sup>41</sup> Obtainable from LANXESS Deutschland GmbH, Business Unit Inorganic Pigments, mailto: ipg.product-information@lanxess.com

 $^{\scriptscriptstyle 45}$  Colour values after matching of the tinting strength parameter Y, i.e.  $\Delta$  L\*=0

<sup>46</sup> Similar to wet system DIN 55983:1983

<sup>53</sup> Minor elements may arise from the raw materials used. However, these are firmly bound to the crystal lattice as ions.



# Bayferrox® 222 FM



### Packaging

The product is available in sacks or bulk bags. For further information please ask your local contact or send an enquiry by e-mail to mailto: ipg.product-information@lanxess.com

## Transport and Storage

| General storage conditions:              | Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature.  |
|--|--|
| Special conditions for opened packaging: | Close bags after use to prevent the absorption of moisture and contamination.  |
| Shelf life:                              | This product has an excellent shelf life. We recommend that this product is used within ten years of the date of manufacture and limit our product warranty to this period. During the first ten years after the date of manufacture we are able to ensure compliance with this specification, provided the material has been stored as stated above and the packaging materials remain undamaged. It must be taken into account that the packaging mean can have a shelf life considerably shorter than the one for this product. All recommendations and warnings given on the packaging must strictly be adhered to. Deviations from storage conditions can lead to undesired changes on side of the packaging materials. These succumb to ageing which may also lead to compromising their capability. Concerning their estimated service life we differentiate between the following packaging materials: |
|  | All kinds of bags (Paper and PE)5 years<br>All kinds of Bulk bag   |
|  | With respect to our Bulk Bags we recommend to avoid UV-radiation<br>because the sewing material of the lifting loops is stabilized against<br>degradation by UV-radiation for appr. 1000 h incident sun radiation<br>for the climate of Central Europe. A more intense sun radiation can<br>shorten this period significantly. In cases of doubt the lifting loops<br>must be checked thoroughly.  |

#### Safety

| Classification         | The product is not classified as dangerous under the relevant EC Directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. |
|------------------------|--|
|                        | In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labelling and transport of dangerous substances must be ensured.                          |
| Additional Information | The safety data sheet should be observed. This contains information on handling, product safety and ecology.   |
|                        | The safety data sheet is available at www.bayferrox.de.  |





## Bayferrox® 222 FM

# Status of Registration (not specified)

| The components of this product are listed on the following inventories: |        |         |            |              |  |
|---|--------|---------|------------|--------------|--|
| Europe:   | USA:   | Canada: | Australia: | New Zealand: |  |
| EINECS  | TSCA   | DSL     | AICS       | NZIOC        |  |
| Philippines:  | Japan: | Korea:  | China:     | Taiwan:      |  |
| PICCS   | METI   | ECL     | IECSC      | NECSI        |  |

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery