

Evonik Corporation DYNACOLL® 7150 Copolyester

Category: Polymer, Thermoset, Polyester, TS

Material Notes:

DYNACOLL® 7000 products are linear copolyesters with primary hydroxyl functionality and medium molecular weight. Our DYNACOLL® 7000 product line is designed as a building block system, allowing the tailormade production of reactive hot melts (RHM). The 7100 series is in a state of amorphous.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-DYNACOLL-7150-Copolyester.php

Physical Properties	Metric	English	Comments
Density	1.26 g/cc	0.0455 lb/in³	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Viscosity	50000 cP	50000 cP	
	@Temperature 130 °C	@Temperature 266 °F	
Molecular Weight	2600 g/mol	2600 g/mol	

Thermal Properties	Metric	English	Comments
Softening Point	85.0 °C	185 °F	
Glass Transition Temp, Tg	50.0 °C	122 °F	
Flash Point	>= 300 °C	>= 572 °F	

Chemical Properties	Metric	English	Comments
Total Acid Number	<= 2.0	<= 2.0	[mg KOH/g]

Descriptive Properties	Value	Comments
Hydroxyl Number (mg KOH/g)	38-46	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China