

## Evonik Corporation DYNACOLL® 7340 Copolyester

Category : Polymer , Thermoset , Polyester, TS

**Material Notes:**

DYNACOLL® 7000 products are linear copolyesters with primary hydroxyl functionality and medium molecular weight. Our DYNACOLL® 7000 product line is designed as a building block system, allowing the tailormade production of reactive hot melts (RHM). The 7300 series is a crystalline

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Evonik-Corporation-DYNACOLL-7340-Copolyester.php](http://www.lookpolymers.com/polymer_Evonik-Corporation-DYNACOLL-7340-Copolyester.php)

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Viscosity	1000 cP	1000 cP	
	@Temperature 130 °C	@Temperature 266 °F	
Molecular Weight	3500 g/mol	3500 g/mol	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	30.0 MPa	4350 psi	with MDI; OH:NCO=1:2.15
Elongation at Break	700 %	700 %	with MDI; OH:NCO=1:2.15

Thermal Properties	Metric	English	Comments
Melting Point	96.0 °C	205 °F	
Softening Point	102 °C	216 °F	
Glass Transition Temp, Tg	-40.0 °C	-40.0 °F	
Flash Point	>= 300 °C	>= 572 °F	

Chemical Properties	Metric	English	Comments
Total Acid Number	<= 2.0	<= 2.0	[mg KOH/g]

Descriptive Properties	Value	Comments
Hydroxyl Number (mg KOH/g)	27-34	

**Contact Songhan Plastic Technology Co.,Ltd.**Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China