

## Evonik Corporation DYNACOLL® 7360 Copolyester

Category : Polymer , Thermoset , Polyester, TS

**Material Notes:**

DYNACOLL® 7000 products are linear copolyesters with primary hydroxyl functionality and medium molecular weight. Our DYNACOLL® 7000 product line is designed as a building block system, allowing the tailormade production of reactive hot melts (RHM). The 7300 series is a crystalline

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Evonik-Corporation-DYNACOLL-7360-Copolyester.php](http://www.lookpolymers.com/polymer_Evonik-Corporation-DYNACOLL-7360-Copolyester.php)

Physical Properties	Metric	English	Comments
Density	1.16 g/cc	0.0419 lb/in <sup>3</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Viscosity	2000 cP	2000 cP	
	@Temperature 80.0 °C	@Temperature 176 °F	
Molecular Weight	3500 g/mol	3500 g/mol	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	25.0 MPa	3630 psi	with MDI; OH:NCO=1:2.8
Elongation at Break	400 %	400 %	with MDI; OH:NCO=1:2.8

Thermal Properties	Metric	English	Comments
Melting Point	55.0 °C	131 °F	
Softening Point	63.0 °C	145 °F	
Glass Transition Temp, Tg	-60.0 °C	-76.0 °F	
Flash Point	>= 300 °C	>= 572 °F	

Chemical Properties	Metric	English	Comments
Total Acid Number	<= 2.0	<= 2.0	[mg KOH/g]

Descriptive Properties	Value	Comments
Hydroxyl Number (mg KOH/g)	27-34	

**Contact Songhan Plastic Technology Co.,Ltd.**Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China