

Evonik Corporation DYNACOLL® 7362 Copolyester

Category : Polymer , Thermoset , Polyester, TS

Material Notes:

DYNACOLL® 7000 products are linear copolyesters with primary hydroxyl functionality and medium molecular weight. Our DYNACOLL® 7000 product line is designed as a building block system, allowing the tailormade production of reactive hot melts (RHM). The 7300 series is a crystalline

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-DYNACOLL-7362-Copolyester.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Viscosity	500 cP	500 cP	
	@Temperature 80.0 °C	@Temperature 176 °F	
Molecular Weight	2000 g/mol	2000 g/mol	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	25.0 MPa	3630 psi	with MDI; OH:NCO=1:2.7
Elongation at Break	400 %	400 %	with MDI; OH:NCO=1:2.7

Thermal Properties	Metric	English	Comments
Melting Point	53.0 °C	127 °F	
Softening Point	60.0 °C	140 °F	
Glass Transition Temp, Tg	-60.0 °C	-76.0 °F	
Flash Point	>= 200 °C	>= 392 °F	

Chemical Properties	Metric	English	Comments
Total Acid Number	<= 2.0	<= 2.0	[mg KOH/g]

Descriptive Properties	Value	Comments
Hydroxyl Number (mg KOH/g)	47-54	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China