

Evonik Corporation DYNACOLL® 7365 Copolyester

Category : Polymer , Thermoset , Polyester, TS

Material Notes:

DYNACOLL® 7000 products are linear copolyesters with primary hydroxyl functionality and medium molecular weight. Our DYNACOLL® 7000 product line is designed as a building block system, allowing the tailormade production of reactive hot melts (RHM). The 7300 series is a crystalline

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-DYNACOLL-7365-Copolyester.php

Physical Properties	Metric	English	Comments
Density	1.16 g/cc	0.0419 lb/in ³	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Viscosity	10000 cP	10000 cP	
	@Temperature 80.0 °C	@Temperature 176 °F	
Molecular Weight	6500 g/mol	6500 g/mol	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	20.0 MPa	2900 psi	with MDI; OH:NCO=1:2.9
Elongation at Break	300 %	300 %	with MDI; OH:NCO=1:2.9

Thermal Properties	Metric	English	Comments
Melting Point	57.0 °C	135 °F	
Softening Point	63.0 °C	145 °F	
Glass Transition Temp, Tg	-60.0 °C	-76.0 °F	
Flash Point	>= 300 °C	>= 572 °F	

Chemical Properties	Metric	English	Comments
Total Acid Number	<= 2.0	<= 2.0	[mg KOH/g]

Descriptive Properties	Value	Comments
Hydroxyl Number (mg KOH/g)	14-20	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China