

## Evonik Corporation DYNACOLL® 7380 Copolyester

Category : Polymer , Thermoset , Polyester, TS

**Material Notes:**

DYNACOLL® 7000 products are linear copolyesters with primary hydroxyl functionality and medium molecular weight. Our DYNACOLL® 7000 product line is designed as a building block system, allowing the tailormade production of reactive hot melts (RHM). The 7300 series is a crystalline

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Evonik-Corporation-DYNACOLL-7380-Copolyester.php](http://www.lookpolymers.com/polymer_Evonik-Corporation-DYNACOLL-7380-Copolyester.php)

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in <sup>3</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Viscosity	2000 cP	2000 cP	
	@Temperature 80.0 °C	@Temperature 176 °F	
Molecular Weight	3500 g/mol	3500 g/mol	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	20.0 MPa	2900 psi	with MDI; OH:NCO=1:2.12
Elongation at Break	20 %	20 %	with MDI; OH:NCO=1:2.12

Thermal Properties	Metric	English	Comments
Melting Point	70.0 °C	158 °F	
Softening Point	77.0 °C	171 °F	
Flash Point	>= 300 °C	>= 572 °F	

Chemical Properties	Metric	English	Comments
Total Acid Number	<= 2.0	<= 2.0	[mg KOH/g]

Descriptive Properties	Value	Comments
Hydroxyl Number (mg KOH/g)	27-34	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**