

Evonik Corporation VESTOPLAST® 206 B Amorphous Polyalphaolefin

Category : Polymer , Thermoplastic , Polyalphaolefin

Material Notes:

VESTOPLAST 206 is a reactive, silane grafted, amorphous polyalphaolefin. It causes a high adhesion to substrates such as glass, ceramics, metals and polar plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-VESTOPLAST-206-B-Amorphous-Polyalphaolefin.php

Physical Properties	Metric	English	Comments
Density	0.870 g/cc	0.0314 lb/in ³	DIN 53 482
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Viscosity	6000 cP	6000 cP	melt; DIN 53 019
	@Temperature 190 °C	@Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	1.90 MPa	276 psi	DIN EN ISO 527-3
Elongation at Break	720 %	720 %	DIN EN ISO 527-3
Penetration	20	20	needle 100/25/5; DIN 52 010
	@Thickness 0.100 mm	@Thickness 0.00394 in	

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-34.0 °C	-29.2 °F	DIN 53 765
Ring & Ball Softening Point	104 °C	219 °F	DIN 52 011

Descriptive Properties	Value	Comments
Open Time (sec)	50	Degussa Method
Setting Time (sec)	1	Degussa Method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China