

PRASAD INTERNATIONAL LIMITED



REACH Status :

| Product Description | | | | | | |
|--|---------------|------------------|---------------|--|--|--|
| CI Generic Name | Middle Chrome | PIL Product Code | PRPL 2002 | | | |
| CI No. | 77600 - 77603 | CAS No. | 1344-37-2 | | | |
| EINECS No. | 215-693-7 | Chemical Type | Chrome Yellow | | | |
| Molecular Formula | PbCrO4+PbSO4 | Molecular Weight | 576.07 | | | |
| Chemical Name: lead sulfochromate vellow | | | | | | |

Physical Properties

| Sieve Residue (PPM) Max. | 1000 |
|---------------------------|---------|
| Oil Absorption(gms) | 20 - 35 |
| Bulk Density(gm/ml) | 100 |
| Salt Content (%) Max. | 1 |
| Moisture Content (%) Max. | 1 |
| PH Value | 5-6 |

| Mass Tone : 1 % | Tint Tone : 1:1 Ratio |
|-----------------|-----------------------|
| | |
| | |
| | |
| | |
| | |
| | |
| | |
| | |

| Fastness properties | | Specification | | |
|---------------------|--------------|----------------|--|------------------------|
| Heat °C | PP-Mass Tone | 210°C / 5 min. | Coloristic properties | Strength : ± 5 % |
| Heat °C | PP-Tint Tone | 210°C / 5 min. | Coloristic properties | DA,DB,DE,DC,DH,DL: ± 1 |
| Light | Mass Tone | 7 | Light fastness : Scale 1-8 | 1~Poor & 8 ~ Excellent |
| Light | Tint Tone | | Weather fastness : Scale 1-5 | 1~Poor & 5 ~ Excellent |
| Weather | Mass Tone | - | Migration : Scale 1-5 | 1~Poor & 5 ~ Excellent |
| Weather | Tint Tone | - | Heat Stability °C DE≤ 3 at Maximum Temp with dwell time 5 minutes. | |
| Migration | | 5 | | |

Application

Polyolefin, PVC, PS

The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Regd. Office: 601-602, Surya Rath, Panchvati, 1st. Lane, Opp. White House, Ambawadi, Ahmedabad-380 006, Gujarat, India**Phone:** +91-79-26422349/26425650**Fax:** +91-79-26562870**E-mail:** techservices@prasadinternational.com