

PRASAD



Revision : 00

**INTERNATIONAL LIMITED** 

## **REACH Status : P.B.29 is Pre Registered**

Date : 24.01.2014

Product Description		
Product	MONOPIL W-PE BLUE 29	
PIL Product Code	PRMO-WPE 2006	
Color Index No.	77007	

Physical Properties		Mass Tone : 0.2 %	Tint Tone : 1:5 Ratio
Appearance	Bright Blue Granules		
Bulk Density(gm/ml)	0.70 - 0.90		
Pigment Loading	65 %		

Fastness properties		
Heat °C	PP-Mass Tone	270°C / 5 min.
Heat °C	PP-Tint Tone	290°C / 5 min.
Light	Mass Tone	8
Light	TintTone	8
Migratior	1	4-5

Specification		
Coloristic properties (Tint)	Strength : ± 5 %	
Coloristic properties (Tint)	DA,DB,DE,DC,DH,DL: ± 1	
Light fastness : Scale 1-8	1~Poor & 8 ~ Excellent	
Migration : Scale 1-5	1~Poor & 5 ~ Excellent	
Heat Stability °C	DE ≤3 at Maximum Temp. With dwell time 5 minutes.	

## Application

Polyolefin

Note: The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade. The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

 Regd. Office:
 601-602, Surya Rath, Panchvati, 1st. Lane, Opp. White House, Ambawadi, Ahmedabad-380 006, Gujarat, India

 Phone:
 +91-79-26422349/26425650 Fax: +91-79-26562870

 E-mail:
 techservices@prasadinternational.com