

Evonik Corporation Vestamid®/Trogamid® RD 5080 HNBR Rubber/Plastic Composite

Category : Polymer , Thermoplastic

Material Notes:

FormulationZetpol® 3110

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-VestamidTrogamid-RD-5080-HNBR-RubberPlastic-Composite.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	>= 0.32	>= 0.32	Rheometer, t₁₀
	@Temperature 170 °C	@Temperature 338 °F	
	>= 2.0	>= 2.0	Rheometer, t₉₀
	@Temperature 170 °C	@Temperature 338 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	79	79	
Tensile Strength at Break	21.2 MPa	3070 psi	
Elongation at Break	154 %	154 %	
100% Modulus	0.0128 GPa	1.86 ksi	
Rebound	32 %	32 %	23°C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China