

BYK-3550

Substrate wetting agent and leveling agent based on a silicone acrylate copolymer for solvent-borne coating systems. Strong reduction of the surface tension combined with very good recoatability.

Product Data

Composition

Solution of a silicone-modified polyacrylate

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F):	8.40 lbs/US gal
Non-volatile matter (10 min., 302 °F):	52 %
Solvents:	Methoxypropylacetate
Flash point:	113 °F

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

The product may become turbid at temperatures above 30 °C (86 °F). Please stir before use.
The effectivity of the product is not affected.

Applications

Coatings Industry

Special Features and Benefits

The additive generally provides a strong reduction in the surface tension of the wet coating, which improves substrate wetting and prevents cratering. It also improves leveling. BYK-3550 exhibits a different range of properties depending on the polarity of the system. In polar coatings, it shows an excellent compatibility, which enables homogeneous distribution in the film. In non-polar systems, BYK-3550 has a slight incompatibility, which results in a concentration at the surface of the coating.

Polar systems:

The influence on the surface energy of the cured coating film is negligible. Therefore surface slip is not increased and the recoatability and adhesion of protective foils and adhesives is improved. BYK-3550 can be used in the complete coating structure, from the primer to the top coat. The additive also improves the orientation of matting agents.

Non-polar systems:

BYK-3550 improves the anti-blocking properties, without influencing the recoatability or the gloss.

BYK-3550

Data Sheet
Issue 09/2015

Recommended Use

Industrial coatings	■
Automotive coatings	■
Architectural coatings	■
Can coatings	■
Coil coatings	■

■ especially recommended

Recommended Levels

0.05-0.4 % additive (as supplied) based on the total formulation, for anti-blocking up to 0.6 %.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process; however, post-addition is recommended. It is important to test the compatibility in the respective coating system.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA