

DISPERBYK-166

High molecular weight wetting and dispersing additive for organic pigments in solvent-borne coatings.

Product Data

Composition

Solution of a high molecular weight block copolymer with pigment-affinic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	20 mg KOH/g
Density (68 °F):	8.10 lbs/US gal
Non-volatile matter (20 min., 302 °F):	29.5 %
Solvents:	Butylacetate/methoxypropylacetate 4/1
Flash point:	75 °F

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Special Note

The treatment of some organic pigments can negatively influence the effectiveness of the additive. In these cases, tests with the untreated pigment of the same type may be successful.

Applications

Coatings Industry

Special Features and Benefits

DISPERBYK-166 deflocculates pigments and stabilizes them by means of steric hindrance. It prevents a possible coflocculation, which leads to non-floating coloring in pigment blends. The deflocculating property of the additive results in increased gloss, color strength, transparency or hiding power, and a reduced millbase viscosity.

Recommended Use

The additive is particularly recommended for automotive coatings and should be used for hard-to-disperse pigments (such as DPP types).

Recommended Levels

Amount of additive (as supplied) based on the pigment:

Titanium dioxides: 5-6 %

Organic pigments: 50-80 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Wetting and dispersing additives should generally be added to the millbase. Only in this way can they be fully effective.

Pre-mix the resin and solvent components of the millbase and then gradually let the additive flow in whilst stirring. Add the pigments only after the additive has been thoroughly distributed. In baking coatings, BYK-331 should also be used to improve leveling and to prevent Bénard cells.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SCONA®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany