

# DISPERBYK-170

Wetting and dispersing additive for solvent-borne coil coatings and industrial coatings. Standard additive for acid-catalyzed and acid-curable coating systems.

## Product Data

### Composition

Solution of a high molecular weight block copolymer with pigment affinic groups

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value:	11 mg KOH/g
Density (68 °F):	8.51 lbs/US gal
Non-volatile matter (20 min., 302 °F):	30 %
Solvents:	Methoxypropylacetate/Butylacetate 6/1
Flash point:	97 °F

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Separation or turbidity may occur at temperatures below 0 °C (32 °F). Heat to 20 °C (68 °F) and mix well.

### Special Note

Check the pot life when using in 2-pack polyurethane systems.

## Applications

### Coatings Industry

#### Special Features and Benefits

The additive deflocculates pigments by steric stabilization. As a result of the small particle sizes of the deflocculated pigments, high levels of gloss can be achieved and the color strength is improved. In addition, the transparency is increased in transparent pigments and the hiding power in opaque pigments. The viscosity is reduced. In this way, the flow characteristics are also improved and higher pigment loading is possible. DISPERBYK-170 has an extremely high molecular weight and this results in the outstanding stabilization of inorganic and organic pigments.

## DISPERBYK-170

Data Sheet  
Issue 06/2013

### Recommended Use

DISPERBYK-170 is recommended for industrial coatings and particularly for coil coatings. The preferred fields of application are acid-catalyzed polyester/melamine top coats and PVDF systems.

### Recommended Levels

Additive dosage as supplied based on pigment:

Titanium dioxide: 5-6 %  
Inorganic pigments: 10-20 %  
Organic pigments: 35-70 %  
Carbon blacks: 70-140 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

### Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments.



Additive Guide



**BYK USA Inc.**  
524 South Cherry Street  
P.O. Box 5670  
Wallingford, CT 06492  
USA  
Tel 203 265-2086  
Fax 203 284-9158

[cs.usa@byk.com](mailto:cs.usa@byk.com)  
[www.byk.com/additives](http://www.byk.com/additives)

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA