

Evonik Corporation Vestodur® GF12-FR2 nf PBT (discontinued **)

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Glass Fiber Filled, Flame Retardant

Material Notes:

ISO data as provided by the manufacturer, Creanova, Inc. Glass fiber reinforced (12%), self-extinguishing PBT resin in accordance with UL 94 with non-migrating flame retardants and enhanced rigidity. This former Creanova product line is a part of Degussa AG as of 2001. This grade is not part of the current Degussa product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Evonik-Corporation-Vestodur-GF12-FR2-nf-PBT-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.55 g/cc	0.0560 lb/in ³	
Water Absorption	0.00 %	0.00 %	
Moisture Absorption at Equilibrium	<= 0.50 %	<= 0.50 %	Humidity Absorption
Melt Flow	15 g/10 min	15 g/10 min	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	100 MPa	14500 psi	
Elongation at Break	2.0 %	2.0 %	
Modulus of Elasticity	5.50 GPa	798 ksi	
Charpy Impact Unnotched	2.50 J/cm ²	11.9 ft-lb/in ²	
	2.50 J/cm ²	11.9 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	
	0.500 J/cm ²	2.38 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Tensile Impact Strength	50.0 kJ/m ²	23.8 ft-lb/in ²	
Tensile Creep Modulus, 1 hour	5000 MPa	725000 psi	
Tensile Creep Modulus, 1000 hours	3000 MPa	435000 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	<= 50.0 µm/m-°C	<= 27.8 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	210 °C	410 °F	
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	
Vicat Softening Point	205 °C	401 °F	50°C/hr/50 N
UL RTI, Electrical	130 °C	266 °F	
UL RTI, Mechanical with Impact	130 °C	266 °F	
UL RTI, Mechanical without Impact	130 °C	266 °F	
Flammability, UL94	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Constant	3.0	3.0	
	@Frequency 100 Hz	@Frequency 100 Hz	
	3.0	3.0	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	27.0 kV/mm	686 kV/in	
Dissipation Factor	0.0025	0.0025	
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.016	0.016	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	200 V	200 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China