

DISPERBYK-2000

Wetting and dispersing additive for solvent-borne automotive coatings to stabilize pigments in base coats which contain CAB. Increases the jetness of carbon blacks in automotive coatings.

Product Data

Composition

Solution of a structured acrylate copolymer with pigment-affinic groups


Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	4 mg KOH/g	
Density (68 °F):	8.47 lbs/US gal	
Non-volatile matter (20 min., 302 °F):	40 %	
Solvents:	Methoxypropylacetate/butylacetate	1/1
Flash point:	113 °F	

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.



Applications

Coatings Industry

Special Features and Benefits

DISPERBYK-2000 deflocculates pigments by means of steric stabilization. It also generates a uniform electrical charge in the pigment particles. The resulting repulsion effect and the steric stabilization prevent any coflocculation which leads to non-floating coloring in pigment blends. As a result of the small particle size of the deflocculated pigments, high levels of gloss can be achieved and the color strength is improved, transparency is increased in transparent pigments and hiding power is increased in opaque pigments. In the case of fine-particle carbon blacks, DISPERBYK-2000 produces a significant improvement in the jetness of carbon blacks. Furthermore, the viscosity is reduced which improves the leveling properties and enables a higher pigment load.

Recommended Use

DISPERBYK-2000 is particularly recommended for automotive coatings and is suitable for base coats containing CAB and all top coats. It prevents the reflocculation of the pigments even when CAB is added after grinding. For an outstanding grind result it is not necessary to use CAB in the grinding phase.

DISPERBYK-2000

Data Sheet
Issue 03/2014

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments:	12-17 %
Titanium dioxides:	5 %
Organic pigments:	20-70 %
Carbon blacks:	70-140 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. Pre-mix the resin and solvent components of the millbase and then gradually let the additive flow in whilst stirring. Only add the pigments when the additive has been thoroughly distributed. In less polar binder solutions, adding DISPERBYK-2000 produces a brief increase in viscosity. This is product-specific and has no influence on the final dispersing result. The brief increase in viscosity can be prevented by adding small quantities of polar solvent (such as an alcohol or glycol) either to the additive or to the millbase.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ACTAL®, ADJUST®, ADVITROL®, ALUFERSOL®, ANTI-TERRA®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CLAYTONE®, CLOISITE®, COPISIL®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SILBYK®, TIXOGEL®, VISCOBYK®, Y-25®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA